

MATERIAL DATA SHEET

Material name		B-96
Properties	units	value
Al ₂ O ₃ – content	(m/m) %	96
Na ₂ O – content	(m/m) %	max. 0,1
Sintered density	g/cm ³	min. 3,80
Open porosity	%	0
Compressive strenght	MPa	2500
Bending strength	MPa	320
MOHS Hardness	Mohs scale	9
Vickers Hardness	Hv 10	min. 1400
Young's Modulus	GPa	330
Coefficient of linear expansion		
20 to 200 °C	x 10-6 / K	5 – 6
20 to 400 °C		6 – 7
20 to 600 °C		6 – 8
20 to 800 °C		7 – 9,5
20 to 1000 °C		7 – 8,5
Specific Heat	J/kg*K	800 – 900
Thermal Conductivity (20-100°C)	W/m*K	18 – 24
Water Absorption	%	0
Electric strength	kV/mm	15
Thermal shock resist	ΔT°C	200
Colour		white

THE INFORMATION IN THIS DATA SHEET IS FOR DESIGN GUIDANCE ONLY.
BAKONY TECHNICAL CERAMICS LTD. DOES NOT WARRANTY THIS DATA AS
ABSOLUTE VALUES. FORMING METHODS AND SPECIFIC GEOMETRY COULD
AFFECT PROPERTIES.